

In the Specification:

Replace the paragraph at page 12, lines 11-16, with the following rewritten paragraph:

In general, the functionalized impact copolymer will have at least 1% acid or acid derivative grafted. More typically the grafted impact copolymer will contain 1.75 to 3.5% and, more preferably, 2 to 3% of the graft monomer and the graft to MFR ratio will be 0.5 or higher and, more preferably, 1 or above. Grafted impact copolymers having graft to MFR ratios of 1 and above are disclosed in ~~copending U.S. patent application Serial No. 10/222,568~~ U.S. Patent No. 6,716,928 which is incorporated herein by reference.